

What is claimed is:

1) A composition of matter useful as a phosphor in light emitting diodes, which comprises a material described by the formula:



in which:

M comprises one or more elements selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn,

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on the total molar weight of said composition, and wherein x and y are each independently any value between 0 and 1, subject to the proviso that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25.

2) A composition according to claim 1 wherein $0 \leq x \leq 1$ and $0 \leq y \leq 1$.

3) A composition according to claim 1 wherein $0.5 \leq x \leq 1$ and $0 \leq y \leq 0.5$.

4) A composition according to claim 1 wherein $0 \leq x \leq 0.5$ and $0 \leq y \leq 0.5$.

- 5) A composition according to claim 1 wherein $0 \leq x \leq 0.5$ and $0.5 \leq y \leq 1.0$.
- 6) A composition according to claim 1 wherein x is about 0, and y is about 1.
- 7) A composition according to claim 1 wherein x is about 1, and y is about 0.
- 8) A composition according to claim 1 wherein M comprises zinc and strontium.
- 9) A composition according to claim 8 having the formula $Zn_uSr_vGa_2(S_xSe_y)_4:Eu$ in which u is about 0.71; v is about 0.29; x is about 0.615; and y is about 0.385.
- 10) A composition comprising at least two different phosphors according to claim 1.

11) A light emitting device comprising:

- a) a light source selected from the group consisting of: light-emitting diodes and lasers, wherein said light source emits light having a wavelength of between about 360 and about 480 nanometers; and
- b) a phosphor described by the formula:



in which:

M comprises one or more elements selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn,

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on the total molar weight of said composition, and wherein x and y are each independently any value between 0 and 1, subject to the proviso that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25.

12) A light emitting device according to claim 11, wherein said phosphor emits white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

13) A light emitting device according to claim 11 comprising a mixture of at least two different phosphors described by said formula.

14) A light emitting device according to claim 13, wherein said mixture of phosphors emit white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

15) A light emitting device according to claim 11 which comprises a phosphor having the formula $Zn_uSr_vGa_2(S_xSe_y)_4:Eu$ in which u is about 0.71; v is about 0.29; x is about 0.615; and y is about 0.385.

16) A composition of matter useful as a phosphor in light emitting diodes, which comprises a material described by the formula:



in which:

M comprises one or more elements selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn,

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on the total molar weight of said composition, and wherein x and y are each independently any value between 0 and 1, subject to the proviso that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25.

17) A composition according to claim 16 wherein $0 \leq x \leq 1$ and $0 \leq y \leq 1$.

18) A composition according to claim 16 wherein $0.5 \leq x \leq 1$ and $0 \leq y \leq 0.5$.

19) A composition according to claim 16 wherein $0 \leq x \leq 0.5$ and $0 \leq y \leq 0.5$.

20) A composition according to claim 16 wherein $0 \leq x \leq 0.5$ and $0.5 \leq y \leq 1.0$.

- 21) A composition according to claim 16 wherein x is about 0, and y is about 1.
- 22) A composition according to claim 16 wherein x is about 1, and y is about 0.
- 23) A composition according to claim 16 having the formula $\text{Ba}_u\text{Sr}_v\text{Ga}_4(\text{S}_x\text{Se}_y)_7\text{:Eu}$ in which u is about 0.78, v is about 0.22, x is about 0.88; and y is about 0.12.
- 24) A composition comprising at least two different phosphors according to claim 16.

25) A light emitting device comprising:

- a) a light source selected from the group consisting of: light-emitting diodes and lasers, wherein said light source emits light having a wavelength of between about 360 and about 480 nanometers; and
- b) a phosphor described by the formula:



in which:

M comprises one or more elements selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn,

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on the total molar weight of said composition, and wherein x and y are each independently any value between 0 and 1, subject to the proviso that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25.


26) A light emitting device according to claim 25, wherein said phosphor emits white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

27) A light emitting device according to claim 25 comprising a mixture of at least two different phosphors described by said formula.

28) A light emitting device according to claim 27, wherein said mixture of phosphors emit white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

29) A light emitting device according to claim 25 which comprises a phosphor having the formula $\text{Ba}_u\text{Sr}_v\text{Ga}_4(\text{S}_x\text{Se}_y)_7:\text{Eu}$ in which u is about 0.78, v is about 0.22, x is about 0.88; and y is about 0.12.

30) A composition of matter useful as a phosphor in light emitting diodes, which comprises a material described by the formula:



in which:

M1 comprises an element selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

M2 comprises an element selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn

which is different from M1;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn;

wherein p can be either about 2 or about 4, and q can be either about 4 or about 7, subject to the provisos that when p is about 2, q is about 4 and when p is about 4, q is about 7;

wherein x and y are each independently any value between 0 and 1, subject to the provisos that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25, the sum of m and n is about 1; and

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on the total molar weight of said composition.

- 31) A composition according to claim 30 wherein $0 \leq x \leq 1$ and $0 \leq y \leq 1$.
- 32) A composition according to claim 30 wherein $0.5 \leq x \leq 1$ and $0 \leq y \leq 0.5$.
- 33) A composition according to claim 30 wherein $0 \leq x \leq 0.5$ and $0 \leq y \leq 0.5$.
- 34) A composition according to claim 30 wherein $0 \leq x \leq 0.5$ and $0.5 \leq y \leq 1.0$.
- 35) A composition according to claim 30 wherein x is about 0, and y is about 1.
- 36) A composition according to claim 30 wherein x is about 1, and y is about 0.
- 37) A composition according to claim 30 wherein M comprises zinc and strontium.
- 38) A composition comprising at least two different phosphors according to claim 30.
- 39) A light emitting device comprising a phosphor according to claim 30.
- 40) A light emitting device according to claim 39, wherein said phosphor emits white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

41) A light emitting device according to claim 39 comprising a mixture of at least two different phosphors described by said formula.

42) A light emitting device according to claim 41, wherein said mixture of phosphors emit white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.